

A **U.L recognized**, flame retardant, mineral filled, glass fiber reinforced polyester **thermoset molding compound** suitable for compression, transfer, and injection molding. It is currently supplied in bulk form, cut preforms and box length extrusions.

MOLDED PROPERTIES

UL File E107977

PHYSICAL / THERMAL

	<u>TYPICAL</u>		<u>VALUES</u>	
	SI	SI	US	US
Impact strength (D 256)	J/m	267 - 374	ft-lb/in	5.0 - 7.0
Flexural strength (D 790)	MPa	76 - 97	psi	11,000-14,000
Tensile strength (D 638)	MPa	57.00	psi	8,300
Heat Deflection Temp. (D 648)	°C	>260	°F	>500
Molding temperature	°C	140 - 176	°F	285 - 350
Molding pressure	bar	70 - 140	psi	1000 - 2000
Mold shrinkage (D 955)	mm/mm	.002-.003	in/in	.002-.003
Specific gravity (D 792)				1.95
Flammability (UL 94 @ 1/16")				V-0
Barcol Hardness				35 - 45
Water absorption (D 570) by weight 24 hours			%	0.06
168 hours			%	0.20

ELECTRICAL

	SI	SI	US	US
Arc resistance (D 495)	Seconds	>190	Seconds	>190
Volume resistivity (D 257)	ohm-cm	1.29X 10 ¹⁵		
Dielectric strength (D 149)	kV/mm	>20	v/mil	>500
Comparative tracking index (D3638)			v	>600

The above data was generated based on a specific typical formulation. Variations to satisfy customer requirements may result in different values.

IMPORTANT! The information presented herein, while not guaranteed, was prepared by technical personnel and is true and accurate to the best of our knowledge. It is provided for preliminary informational purposes only and for initial evaluation of the product. As a result, they are not appropriate for the purpose of developing a final specification and should not be relied on for such specification purposes. Judgement as to the suitability of the subject molding material for the user's purposes is the user's responsibility. Users shall determine the suitability of the products for their own intended application. No warranty or guaranty, express or implied, is made regarding performance, stability or otherwise. This information is not intended to be all-inclusive as the manner and conditions of use, handling, storage and other factors may involve other or additional safety or performance considerations. While our technical personnel will be happy to respond to questions regarding safe handling and use procedures, safe handling and use remains the responsibility of the customer. No suggestions for use are intended as, and nothing herein shall be construed as a recommendation to infringe any existing patents or to violate any Federal, State or local laws.

